

RED ALDER

SCIENTIFIC NAME: *Alnus rubra*



DISTRIBUTION AND AVAILABILITY





- Coastal Western North America.

COLOR:

Range Variation

Red alder tends to be a light tan to reddish brown; color darkens and reddens with age. There is no visible distinction between heartwood and sapwood. Small sound knots and large aggregate rays appear as occasional small streaks on the face grain that are not considered as defects in the wood.



DISCLAIMER

A single sample may not accurately represent the full range of natural variations to be expected. Due to the inherent properties and characteristics of wood, these samples should be viewed as an approximation of what can be obtained. Some wood species have more natural variance in appearance than others. We have made every effort to make colors as accurate as possible. Colors on screen may vary depending on your screen setting and resolution.

RED ALDER INFORMATION

AVERAGE DRIED WEIGHT

28 lbs/ft³ (450 kg/m³)



GRAIN | TEXTURE

The wood has fairly straight grain, and is fine-grained and even-textured.




PRICING | AVAILABILITY

Low to Moderate. *Readily Available*



COVERED EXTERIOR RATING

Poor | Good | Excellent



PHOTOSENSITIVITY

High | **Moderate** | Low



CONSERVATION STATUS

LC - Least Concern (IUCN 3.1)



VENEER OPTIONS

Rotary Cut | Flat Cut | Quarter Cut

CONTACT OUR TEAM

T 604-776-2265

2320 Peardonville Road, Abbotsford, BC
Canada V2T 6J8

sales@lineaceilings.com lineaceilings.com

