

## RED OAK

SCIENTIFIC NAME: *Quercus rubra*



### DISTRIBUTION AND AVAILABILITY




- Northeastern United States
- Southeastern Canada
- Readily Available

### COLOR:

#### Range Variation

Heartwood is a light to medium brown, commonly with a reddish cast. Paler sapwood is not always sharply demarcated from the heartwood. Quarter cut sections display prominent ray fleck patterns. Rift cutting reduces ray fleck significantly. White oak (*Quercus alba*) tends to have a slightly more olive cast (as opposed to red), but color alone isn't always a reliable method of determining the type of oak.



#### DISCLAIMER

A single sample may not accurately represent the full range of natural variations to be expected. Due to the inherent properties and characteristics of wood, these samples should be viewed as an approximation of what can be obtained. Some wood species have more natural variance in appearance than others. We have made every effort to make colors as accurate as possible. Colors on screen may vary depending on your screen setting and resolution.

# LINEA

## Species Overview

### RED OAK INFORMATION

#### AVERAGE DRIED WEIGHT

44lbs/ft<sup>3</sup> (700 kg/m<sup>3</sup>)



#### GRAIN | TEXTURE

Grain is straight, with a coarse, uneven texture. End grain is very porous




#### PRICING | AVAILABILITY

Moderate. Rift Cut available at a premium. *Readily Available*



#### COVERED EXTERIOR RATING

Poor | Good | **Excellent**



#### PHOTOSENSITIVITY

High | **Moderate** | Low



#### CONSERVATION STATUS

LC - Least Concern (IUCN 3.1)  
G5 - Secure (NatureServe)



#### VENEER OPTIONS

Flat Cut | Quarter Cut | Rift Cut

CONTACT OUR TEAM

T 604-776-2265

2320 Peardonville Road, Abbotsford, BC  
Canada V2T 6J8

sales@lineaceilings.com [lineaceilings.com](https://lineaceilings.com)

